

การสังเคราะห์คาร์บอนนาโนทิวบ์ขนาดเล็กจากแอลกอฮอล์

The Synthesis of Carbon Nanotubes with a Small Diameter Using Alcohol


สุรัชชัย ชัยสิทธิ์ศักดิ์ [1] และ จิติ หนูแก้ว [2]

[1] ห้องปฏิบัติการวิจัยวัสดุและอุปกรณ์นาโนอิเล็กทรอนิกส์
ภาควิชาอิเล็กทรอนิกส์ คณะวิศวกรรมศาสตร์


[2] ภาควิชาฟิสิกส์ประยุกต์ คณะวิทยาศาสตร์

สถาบันเทคโนโลยีพระจอมเกล้าเจ้าคุณทหารลาดกระบัง


Carbons




Diamond




Graphite



Fullerene (C70)







Carbon nanotubes (CNTs)



Multi-walled CNTs


Scientific publications/patents for the CNT area




Source from Science 297(2002)

Synthesis


◆ Arc discharge evaporation
(SWCNT/MWCNT)




◆ Laser vaporization
(SWCNT purity of 70%-90%)



◆ High -pressure carbon monoxide (HiPCo)
(high purity SWCNT)



◆ Chemical vapor deposition (CVD)
(decomposition with thermal,
plasma, hot-filament)



Objective

We report the fabrications of carbon nanotubes by hot filament CVD using alcohol as a carbon source.

The effect of synthesis conditions

- Growth **temperature**
- Type of catalyst material
(Fe-Co with/without **zeolite**)
- Type of alcohol
(**C₂H₅OH** and **CH₃OH**)
- Operate at 1 atm ?

<Characterization: SEM TEM and Raman spectroscopy>


Synthesis methods for SWCNTs

Methods	Growth temperature
CVD	400 • 1200 •

Thermal CVD	<ul style="list-style-type: none">•MWCNT • Temp. • 600 • 800 ••SWCNT • Temp. • 700 • 1200 •
Plasma enhanced CVD (PE-CVD)	<ul style="list-style-type: none">•Low temp. • <400 • ••(Only) MWCNT•Vertically aligned tubes
Hot-filament CVD (HF-CVD)	<ul style="list-style-type: none">•Simplified apparatuses•Possible for Low temp. growth

HF-CVD system.


- C source : **methanol or Ethanol**
- filament temp. : 1600~1800°C
- ds-f: 3 mm
(Sub. Temp.: **550~650 °C**)
- Growth time: 5 min




@room temp.

- Substrates : Si (10x10mm)
- Catalysts : • **1) Fe/Co**
2) Fe/Co+Zeolite

$\text{Fe}(\text{CH}_3\text{COO})_2$, +
 $\text{Co}(\text{CH}_3\text{COO})_2 \cdot 4\text{H}_2\text{O}$ +
Ethanol




Spin-coat




Fe-Co catalysts

$\text{Fe}(\text{CH}_3\text{COO})_2$, +
 $\text{Co}(\text{CH}_3\text{COO})_2 \cdot 4\text{H}_2\text{O}$ +
Zeolite +
Ethanol




Spin-coat



Fe-Co with Zeolite (Y-type)

Dry @ 80°C
18-20 hrs.



Objective


We report the fabrications of carbon nanotubes by hot filament CVD using alcohol as a carbon source.

The effect of synthesis conditions


- Growth **temperature**
- Type of catalyst material
(Fe-Co with/without **zeolite**)
- Type of alcohol
(**C₂H₅OH** and **CH₃OH**)
- Operate at 1 atm ?

<Characterization: SEM TEM and Raman spectroscopy>


Morphologies of CNTs from different thickness of Fe-Co (without zeolite).



(a)




(b)



(c)


Thickness
(a) < (b) < (c)




Fe-Co with zeolite

500nm

CNTs synthesized from **ethanol** at Tsub. **550°C**




(without zeolite)




(with zeolite)

CNTs synthesized from **ethanol** at Tsub. **650°C**




(without zeolite)




(with zeolite)

CNTs synthesized from methanol at Tsub. 650°C




(without zeolite)




(with zeolite)


Raman scattering spectra for the CNTs obtained from methanol at 650°C



CNTs synthesized from **ethanol** at Tsub. **650°C**





(without zeolite)



(with zeolite)

TEM image of CNTs from **ethanol** at Tsub. **650°C**




การเกิดคาร์บอนนาโนทิวป์

Base Growth


Carbon source




Metal catalyst



One Atmosphere HF-CVD System




The influence of T_{sub} on the formation of CNTs



(a). $T_{\text{sub}} : 500-700 \text{ }^{\circ}\text{C}$

CNTs with nano particles.



(b). $T_{\text{sub}} : > 700 \text{ }^{\circ}\text{C}$

Diamond with nano particles.

Conclusions

การทดลองนี้ทำการสร้างคาร์บอนนาโนทิวบ์ (CNTs) โดยวิธี HF-CVD ภายใต้ความดันต่ำ โดยใช้แอลกอฮอล์ 2 ชนิด คือเอทานอล และเมทานอล เป็นแหล่งกำเนิดคาร์บอนและใช้ Fe-Co เป็นโลหะตัวเร่ง จากผลการทดลองพบว่า ชนิดของวัสดุที่นำมาเป็นโลหะตัวเร่ง อุณหภูมิที่ฐานรอง และชนิดของแหล่งจ่ายคาร์บอน มีผลต่อการสังเคราะห์คาร์บอนนาโนทิวบ์ ตัวเร่งผสม Zeolite (Fe-Co ผสม Zeolite) สามารถสังเคราะห์คาร์บอนนาโนทิวบ์ได้ที่อุณหภูมิต่ำกว่าและทิวบ์ที่ได้มีขนาดเล็กกว่า ตัวเร่งที่ไม่ผสม Zeolite (Fe-Co) นอกจากนี้ยังพบว่าเมทานอลสามารถสังเคราะห์คาร์บอนนาโนทิวบ์ที่มีขนาดเล็กได้ดีกว่าเอทานอล ด้วยเงื่อนไขการสังเคราะห์ที่เหมาะสม สามารถสังเคราะห์ทิวบ์ที่มีขนาดเล็ก เส้นผ่าศูนย์กลางประมาณ 0.9 nm ซึ่งได้จากการประมาณจากข้อมูลของ Raman spectroscopy ได้ งานวิจัยนี้อาจใช้เป็นแนวทางในพัฒนาวิธีที่ง่ายและราคาถูกลงสำหรับการสังเคราะห์ คาร์บอนนาโนทิวบ์ในปริมาณมากๆ

กิตติกรรมประกาศ

งานนี้เป็นส่วนหนึ่งของโครงการวิจัยภายใต้การสนับสนุนจาก ศูนย์เทคโนโลยีอิเล็กทรอนิกส์และคอมพิวเตอร์แห่งชาติ (nectec) (NT-B-22-E3-23) ขอขอบคุณนักวิจัยที่ TMEC ดร. อัมพร ดร. เอกลักษณ์ นายนิธิ และนาย วิน สำหรับการ ใช้ FE-SEM และนักวิจัยที่ศูนย์เทคโนโลยีวัสดุแห่งชาติ (mtec) สำหรับการ ใช้ Raman spectroscopy